

Producer	Grade	Particle ave Micron	Permeability D'Arcy	Typical BSI	Wet Density (lbs/ft3)	PH	Diatomite Source	Process	ASBC Test Method
Celite	505	10.9	0.05	Not Tested	24	7	Marine	Calcined	N/A
Celite	505Z	10.9	0.05	35 ppm	24	7	Marine	Calcined	LO-412-433
Celite	Filter-Cel	19.2	0.06	Not Tested	20	7	Marine	Calcined	N/A
Celite	Filter-Cel Z	19.2	0.06	20 ppm	20	7	Marine	Calcined	LO-412-433
Eagle Pitcher	CB-1	20.2	0.08	<20 ppm	24	6.5	?	Calcined	N/A
Eagle Pitcher	CB-2	20.7	0.12	<20 ppm	25	6.5	?	Calcined	N/A
Grefco	SuperAid UF	17	0.13	<20 ppm	28	7	Fresh Water	Calcined	N/A
Eagle Pitcher	CB-3	17.5	0.20	<20 ppm	25	6.5	?	Calcined	N/A
Grefco	SpeedFlow	16.5	0.20	<20 ppm	28	7	Fresh Water	Calcined	N/A
Eagle Pitcher	FP-4	15	0.26	Not Tested	22	9	Fresh Water	Calcined	N/A
Celite	Std. Super-Cel	20.9	0.30	Not Tested	19	7	Marine	Calcined	N/A
Eagle Pitcher	CB-4	20.1	0.35	<30 ppm	25	6.5	?	Calcined	N/A
Grefco	231	28	0.35	<20 ppm		7	Fresh Water	Calcined	N/A
Celite	512Z	16	0.50	20 ppm	19	7	Marine	Calcined	LO-412-433
Celite	512	16	0.50	Not Tested	19	7	Marine	Calcined	N/A
Eagle Pitcher	CB-6	23.5	0.54	<20 ppm	24	7		Calcined	N/A
Eagle Pitcher	FW-6	18	0.56	Not Tested	22	8.2	Fresh Water	Calcined	N/A
Grefco	341	24	0.65	<40ppm	19	8	Fresh Water	Flux-Calcined	N/A
Celite	513	28	0.75	Not Tested	19	10	Marine	Flux-Calcined	N/A
Eagle Pitcher	FW-12	24	0.80	Not Tested	22	9.5	Fresh Water	Calcined	N/A
Eagle Pitcher	CB-12	33.8	1.10	<20 ppm	22	7		Calcined	N/A
Celite	Hyflo Super-Cel Z	30.1	1.10	45 ppm	19	10	Marine	Flux-Calcined	LO-412-433
Celite	Hyflo Super-Cel	30.1	1.10	Not Tested	19	10	Marine	Flux-Calcined	N/A
Eagle Pitcher	FW-14	28	1.20	43 ppm -	22	9	Fresh Water	Flux-Calcined	N/A
Eagle Pitcher	FW-18	31	1.70	Not Tested	22	9.5	Fresh Water	Flux-Calcined	N/A
Celite	503	33.9	2.00	Not Tested	19	10	Marine	Flux-Calcined	N/A
Celite	503 Z	33.9	2.00	35 ppm	19	10	Marine	Flux-Calcined	LO-412-433
Eagle Pitcher	FW-20	33	2.10	Not Tested	22	10	Fresh Water	Flux-Calcined	N/A
Celite	535	42.9	3.00	Not Tested	19	10	Marine	Flux-Calcined	N/A
Celite	535 Z	42.9	3.00	40 ppm	19	10	Marine	Flux-Calcined	LO-412-433
Eagle Pitcher	FW-40	40	3.20	Not Tested	22	10	Fresh Water	Flux-Calcined	N/A
Eagle Pitcher	FW-50	42	3.50	Not Tested	22	10	Fresh Water	Flux-Calcined	N/A
Celite	545	46.5	4.00	Not Tested	19	10	Marine	Flux-Calcined	N/A
Celite	545 Z	46.5	4.00	28 ppm	19	10	Marine	Flux-Calcined	LO-412-433